

ABSTRACT OF THE DISCLOSURE

A molding composition comprising an aggregate
[Component (A)], a linear unsaturated polyester [Component
(B)] and/or linear unsaturated polyester polyamide [Component
5 (C)], and a radical generator [Component (D)], characterized
in that each of Component (B) and Component (C) comprises a
specific alkylene oxide adduct of bisphenol A in an amount of
from 3 to 50 mol% based on the total amount of constituent
monomers of each of Component (B) and Component (C), and a molded
10 article obtained by molding the composition.